

SurfEtch™ Top Surface Retarder

Technical Data Sheet SE-01

FOR PROFESSIONAL USE ONLY. Read all applicable and current product information for your project: Technical Data Sheet (TDS), Color Chart, Installation Guide, Material Safety Data Sheet (MSDS). All information is available for download online at www.butterfieldcolor.com and at point of purchase.

MasterFormat™ Guide Specifications, and Butterfield Color® Architectural Details and Specifications are available for the specifier/designer. All information is available for download online at www.butterfieldcolor.com and at point of purchase.

1. Description: SurfEtch™ Top Surface Retarder is a water-based, biodegradable, low odor top surface retarder. Applied to the surface of fresh concrete, SurfEtch™ Top Surface Retarder chemically delays the set of the surface mortar while allowing the underlying concrete to harden normally. This allows time for washing the surface, producing exposed aggregate flatwork, with subtle and varying reveals of texture and color.

Apply SurfEtch™ Top Surface Retarder on gray concrete or concrete colored with Uni-Mix® Integral Concrete Colorant or Uni-Mix® Liquid Integral Concrete Colorant. Use on poured-in-place flatwork: curbs, sidewalks, driveways, patios, pool decks, tilt-up and precast panels, and most horizontal concrete installations. SurfEtch™ Top Surface Retarder produces a simulated light sand blasted surface exposing the aggregate from 1/16" to 1/8". The fully cured surface is not only attractive, it is also slip resistant. VOC compliant (<10 g/L) and solvent free, SurfEtch™ Top Surface Retarder is safer and cleaner to use compared to acid etching or mechanical blasting. SurfEtch™ Top Surface Retarder is a light blue color to facilitate an even application. Clean tools and equipment with soap and water.

2. Limitations: Apply SurfEtch™ Top Surface Retarder between 55°F to 90°F (13°C to 32°C). Most concrete mix designs stop curing below 50°F. Do not allow the material to freeze during storage or after applied to the concrete. At higher temperatures, low humidity, or windy conditions, the material may prematurely dry and lose its effectiveness unless it is reapplied. Do not apply to concrete that contains cold weather accelerators or hot weather retarders without prior testing. Do not apply to frozen surfaces, nor allow the material to freeze, be-

fore washing to expose the aggregate. Do not use as a finishing aid.

The depth of etch will vary with different mix designs, method and timing of finishing, application consistency, temperature and removal method. Hard-troweled surfaces will reduce the effectiveness of SurfEtch™ Top Surface Retarder. Do not apply to vertical concrete or to form work. Do not apply to shake-on color hardeners, particularly if the surface has a hard-troweled finish, without prior testing and approval. The very dense surfaces typically produced by shake-on color hardener may inhibit the depth of etch compared to a plain concrete surface finished in the same manner.

3. Packaging: SurfEtch™ Top Surface Retarder is available in 1 gal. (3.8 L) and 5 gal. (19 L) pails. Pails should be stored in a cool, dry place when not in use. Do not allow material to freeze. Do not reuse the empty container.

3.1 SHELF LIFE: Shelf life in original, unopened containers is 2 years from the date of purchase.

4. Coverage: SurfEtch™ Top Surface Retarder will cover approximately 175-300 sq. ft./gal. (4.3-7.4 m²/L). Apply at full strength. Do not dilute. Coverage will vary with surface texture and application method.

5. Application Tools: Apply SurfEtch™ Top Surface Retarder with a pump-up sprayer, brush, or roller. Spraying is the most effective and consistent method of application. Use clean equipment free from water or solvent residues. Clean application tools with clean water immediately after use.

6. Installation: Proceed with application after approval of the test area. Utilize the same concrete mix design throughout the installation. Finish the

concrete uniformly level. High or low areas may retain or reject the material, possibly creating inconsistencies in the exposed finish. Concrete with a float or broom finish allows SurfEtch™ Top Surface Retarder to better penetrate the surface compared to hard-troweled concrete. Float open surfaces treated with an evaporation retarder or finishing aid before applying SurfEtch™ Top Surface Retarder. Do not apply the material until bleed water has dissipated. Do not apply curing and sealing compounds before applying SurfEtch™ Top Surface Retarder.

6.1 EXISTING CONCRETE: The cement residue produced when removing SurfEtch™ Top Surface Retarder will bond to hardened concrete. Protect existing concrete by covering it with plastic sheeting or by spraying it with SurfEtch™ Top Surface Retarder. Allow SurfEtch™ Top Surface Retarder to dry completely before proceeding with the new concrete installation. The dried film of SurfEtch™ Top Surface Retarder will prevent the etched residue from penetrating or bonding to the concrete. Protect all adjacent surfaces from discoloration or damage from the chemical etching process.

6.2 APPLICATION: Facilitate mixing by storing the material at moderate temperatures before use. Mix the material with a powered drill, do not hand mix. Mix at low speeds until the material is a uniform light blue color. Mixing time for a 5 gal. pail is 3-5 minutes. Apply an even coating of SurfEtch™ Top Surface Retarder to the concrete's surface. When spraying, utilize the lowest pressure possible to create a fan pattern. Apply the material evenly, to achieve a masking, consistent blue color over the concrete. If an insufficient amount of top surface retarder is applied, premature



SurfEtch™ Top Surface Retarder

Technical Data Sheet SE-01

Engineered Concrete Performance
BUTTERFIELD
COLOR
 3 CONCRETE FINISHES

drying may occur, which could effect the exposure results. Heat, wind, and low humidity may also contribute to excessive drying. Cover the concrete surface completely with SurfEtch™ Top Surface Retarder. For consistent exposure results, spray all concrete surfaces at the same time after completing concrete finishing.

6.3 DWELL TIME: Do not work the surface with a float or trowel after applying SurfEtch™ Top Surface Retarder. The material will dry in 1-2 hours, after which time it is resistant to light rain. Prior to drying, protect SurfEtch™ Top Surface Retarder from rain by temporarily covering it with plastic and then removing as soon the weather allows. Divert downspouts or other sources of substantial water exposure from flowing directly on the concrete after applying SurfEtch™ Top Surface Retarder. Do not apply curing compounds over the surface retarder.

6.4 REMOVAL AND EXPOSURE: Expose the aggregate by washing it within 6-24 hours after application, depending upon the temperature and humidity, and as determined by the approved mock-up panel. Use a garden hose and a new, clean broom or pressure washer to work the surface. Work a small area. If the depth of reveal is too deep, stop washing and allow the concrete to cure and harden further. Some concrete mix designs installed during elevated temperatures may require exposure to start sooner than 12 hours. Cold temperatures delay exposure. Achieve uniform exposure by washing the surface at the same time after the initial application of SurfEtch™ Top Surface Retarder to the concrete.

7. Curing and Sealing: Allow the concrete to dry (no visible moisture or dampness) for 12-24 hours before applying a liquid curing compound. Use Clear Guard® Cure and Seal for exterior applications or interiors when a strong odor is not a concern. Clear Guard® H₂O Cure and Seal is a water-based system useful for interior and exterior applications. Multiple light coats are necessary over the roughened etched surface. Do not allow the material to puddle on the surface or in the joints.

To protect the exposed aggregate finish, reseal the concrete with Clear Guard® Cure and Seal, or Clear Guard® H₂O Cure and Seal. Reapplication over time may cause the surface to become slippery. If this occurs, stripping the sealer will be required. Thoroughly remove coatings from concrete with Butterfield Color® Delaminator™.

Read all applicable product Technical Data Sheets before using materials. All information is available for download online at www.butterfieldcolor.com and at point of purchase.

8. Quality Control: Create a job site sample at least 21 days before installation for approval. Utilize all materials, tools, and techniques from the actual job in the job site sample. When curing and sealing the surface, verify adequate wet and dry slip resistance of the sealed surface. Verify maintenance requirements. Site visits by Butterfield Color, Inc. Personnel are for making technical recommendations only and not for supervising or providing quality control.

WARNING: MAY CAUSE EYE, SKIN, AND RESPIRATORY IRRITA-

TION. DO NOT TAKE INTERNALLY. KEEP OUT OF REACH OF CHILDREN AND ANIMALS. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING DURING APPLICATION. ENSURE ADEQUATE VENTILATION DURING AND AFTER APPLICATION. IN CASE OF SPILLAGE, ABSORB AND DISPOSE OF THE MATERIAL IN ACCORDANCE WITH LOCAL, STATE, AND FEDERAL REGULATIONS. BEFORE USE, READ THE MATERIAL SAFETY DATA SHEET. ALL INFORMATION IS AVAILABLE FOR DOWNLOAD ONLINE AT WWW.BUTTERFIELDCOLOR.COM AND AT POINT OF PURCHASE.

LIMITED WARRANTY AND DISCLAIMER – EXCLUSIVE REMEDY: Butterfield Color, Inc. (“BC”) warrants that this product conforms to its published specifications when it is shipped. THIS LIMITED WARRANTY IS THE EXCLUSIVE WARRANTY AND THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. BC does not warrant any particular method of use or application of the product or its performance under any particular condition. If this product does not conform to its published specifications when shipped, we will replace the product as your exclusive remedy. Any action for breach of the limited warranty or any other liability arising from this product must be brought within 90 days of receiving the product. BC is not liable for consequential damages or personal injury arising from the use, storage or handling of this product.

Suggested Short Form Specification for Butterfield Color® SurfEtch™ Top Surface Retarder:

Protect adjacent surfaces not receiving top surface retarder with plastic sheeting and double tape. Apply even coat of Butterfield Color® SurfEtch™ Top Surface Retarder according to manufacturer's instructions and recommended coverage rate, to achieve a masking, consistent, blue color over concrete surface. Allow top surface retarder to remain on concrete surfaces for a period established by the mock-up. Expose the aggregate by washing off the top surface retarder within 6 to 24 hours after application, using a garden hose or pressure washer and working the surface with new, clean brooms. If etching is too deep, allow concrete to further cure. Clean tools immediately after use. Clean spillage and residue from adjacent surfaces. Dispose of residue legally. Seal concrete with 2 coats of Butterfield Color® Clear Guard® Cure and Seal with a slip-resistive additive according to manufacturer's instructions.

Engineered Concrete Performance
BUTTERFIELD
COLOR
 3 CONCRETE FINISHES