

# Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal

## Technical Data Sheet CGHPWCAS-06

625 W Illinois Ave  
Aurora, IL 60506  
Phone: 800-282-3388  
Fax: 630-906-1982  
www.butterfieldcolor.com

**FOR PROFESSIONAL USE ONLY.** Read all applicable and current product information for your project: Technical Data Sheet (TDS), Color Chart, Installation Guide, Safety Data Sheet (SDS). All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) or at 800-282-3388.

MasterFormat™ Guide Specifications, and Butterfield Color® Architectural Details and Specifications are available for the specifier/designer. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) or at 800-282-3388.

**1. Product Description:** Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal is a water-based, VOC compliant, non-yellowing, curing, and sealing compound for newly poured and existing concrete surfaces. The product is formulated for curing and sealing uncolored concrete, integrally colored concrete, and color hardened (shake-on) concrete, stamped and/or stenciled concrete, as well as cementitious overlays. It is suitable for residential or commercial projects, interior floors, exterior hardscapes, and vertical surfaces.

Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal visually enhances the concrete color, protects the surface from dirt and staining, and minimizes the affects of de-icing salts and exposure to gas or oil. It is well suited for application to cured concrete to prevent absorption or penetration of many fats, oils, greases, aliphatic solvents, salts, acids, and other chemicals. By preventing penetration of these compounds, Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal provides good economical protection for floors and hardscapes, thereby reducing maintenance costs.

As a curing compound, it improves the surface strength, abrasion resistance, and durability of the concrete, and reduces the potential for plastic cracking. It forms a moisture barrier that prevents free lime in the concrete from migrating and reacting at the surface, forming a dust residue. Curing with Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal also provides interim construction protection from most oils, greases, chemical spills, and from the adhesion of mortar splashes. Final cleanup costs are reduced and the resulting concrete surface appearance is greatly enhanced. Clear Guard® H<sub>2</sub>O PLUS+ Water-

Based Cure and Seal can also be applied to old concrete, terrazzo, brick, and masonry tiles to dust proof and impart stain and chemical resistance.

Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal is an emulsified acrylic specifically designed to meet the moisture retention properties of ASTM C-309, AASHTO M-148, Navdock 13 YF, and ORD C-300, when applied at the recommended coverage rate. It is a milky white liquid which dries to a clear, high gloss, UV resistant film. Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal complies with VOC (<100 g/L) requirements and other Federal and State Air Quality Regulations. The longevity of Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal depends upon the dried film thickness, exposure, and use conditions. Clear sealers will scratch and scuff, and will require maintenance. Treated surfaces are readily re-coated after thorough cleaning.

**2. Limitations:** Do not use Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal on concrete slabs with inadequately drained sub-grade and/or surfaces subject to hydrostatic water pressures. Do not use in swimming pools, fountains or ponds. Do not use on surfaces that will have direct food contact. Do not use for re-coating or in conjunction with other floor sealers, treatments, bond breakers, or adhesives without prior test to determine compatibility and adhesion. Do not apply solvent-based sealers over Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal. Do not use to fill or repair cracks in the substrate.

Do not use Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal if it has been frozen. Do not apply at or below 45°F (7°C) or when such tempera-

tures are expected within 12 hours following application. Do not over-apply material or allow to collect in joints, texture imprints or other surface impressions. Excess material may whiten permanently and lose adhesion.

**Warning: Treated surfaces may be slippery during application prior to drying, and when wet with water or liquids after drying. Concrete should be textured sufficiently to eliminate potential slipping hazards. In addition, use a non-slip additive with the Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal. Interior floors may be maintained with a slip resistant wax. Test and confirm that the treated surface is adequately slip resistant prior to opening installation to any traffic.**

**3. Chemical Resistance:** Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal provides 24-hour spot resistance to the following chemicals with little, if any, coating effect:

<i>antifreeze</i>	<i>deicing salts</i>
<i>foods</i>	<i>fruit juices</i>
<i>vegetable oil</i>	<i>calcium chloride</i>
<i>sodium chloride</i>	

A test application should be made on the job site concrete to determine the chemical and stain resistance of Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal.

#### 4. Packaging:

Container	Content
Pail	5 US gallons (19.0 L)

**4.1 SHELF LIFE:** 1 year, when stored in original, unopened containers, in dry storage, between 60°-80°F. Do not use material that has been frozen.

**5. Coverage:** Coverage rates vary with surface texture and porosity, ambient and surface temperatures, method of application. The following



# Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal

## Technical Data Sheet CGHPWCAS-06

coverage rates are approximate for broom finish concrete surfaces:

Curing: 200 sq. ft./gal. (4.9 m<sup>2</sup>/L)

Sealing: 200-400 sq. ft./gal. (4.9-9.8 m<sup>2</sup>/L)

Avoid excessive build-up, particularly in the depressed textures and grout joints of stamped or stenciled concrete, hand tooled or saw cut joints. Thicker applications may lead to discoloration and diminished sealer performance. Wipe up or brush out excessive material before the film becomes tacky.

**6. Application:** Premix Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal before using. Do not dilute or mix with any other liquid or chemical. Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal may be applied using a roller, hand pump sprayer, or an airless sprayer. If using a roller, a non-shed roller with 1/4"-1/2" nap length is recommended. The nap length of the roller will depend on the surface porosity and texture of the concrete. Best results are obtained when product is applied at substrate temperatures in excess of 50°F (10°C). Do not apply at or below 45°F (7°C) or when such temperatures are expected within 12 hours following application. Control interior environment to prevent condensation from forming on the surface prior to sealing and before the sealer has become tack free. Do not apply if there are concerns with the quality of the color or finish of the concrete, until those concerns are adequately addressed.

When using a sprayer, apply material with a fan pattern nozzle. Spray equipment should be clean and in good working condition. Hand pump sprayers must be capable of delivering moderately viscous liquids. Maintain a wet edge and avoid excessive overlaps of material. Care must be taken to protect adjacent areas from over spray.

When used as a cure coat or as an initial seal coat, if additional protection or gloss is required, an additional coating may be applied 12-24 hours after the cure coat or seal coat

has dried. Longer drying times will be necessary at low temperatures or high humidity.

**6.1. NEW CONCRETE: UNCOLORED, INTEGRALLY COLORED, COLOR HARDENED:** Apply Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal immediately following final finishing and after the slab is firm enough to walk on without damage. Do not apply if bleed water is present. Apply to vertical surfaces immediately following form removal. Avoid runs or puddles and over application. To achieve maximum sealing and dust-proofing benefits, a second application should be made at least two weeks after the cure coat application. Surfaces to be retreated should be clean and dry. Apply in a continuous wet surface film. Application of product over excessively smooth, hard-troweled surfaces may result in adhesion loss.

**6.2. NEW COLORED, STAMPED, OR STENCILED CONCRETE:** After concrete has been stamped using Perma-Cast® Antiquing Release agent, thoroughly remove the residual release powder by washing and scrubbing. The concrete should be allowed to dry thoroughly before applying Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal. If Perma-Cast® Clear Liquid Release or mineral spirits is used, do not use Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal. Read the Perma-Cast® Antiquing Release and the Perma-Cast® Clear Liquid Release Technical Data Sheets before applying products. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) or at 800-282-3388.

**6.3. EXISTING CONCRETE AND OVERLAYS:** Adequately remove accumulations of grease, oil residue, incompatible curing, or sealing compound residue and other substances that would diminish adhesion. Wash surfaces thoroughly. Allow surface and joints to adequately dry before applying Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal. Smooth troweled interior floors will require

mechanical sanding to ensure the penetration and adhesion. Surfaces that resist penetration and immediate darkening with water is an indication that surface preparation is required. Very rough, porous and deeply textured surfaces may require multiple thin applications to ensure the formation of a protective film, without pinholes or holidays.

**6.4 NEW T1000® FINE OVERLAY AND T1000® STAMPABLE OVERLAY:** Interior floors and exterior hard-scapes that have been resurfaced should be cured 12-24 hours after installation at 70°F (21°C) before applying Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal.

Before application of sealer the Moisture Vapor Emission Rate (MVER) of the concrete or cementitious topping must be measured and be less than 5 pounds per 1000 square feet per 24 hours (2.3 kg/92.9 m<sup>2</sup>/24 hours). Promptly clean application equipment with soap and water following use. Handle and dispose of cleaning residue properly.

**7. Dry Time:** Drying times will vary depending upon wet film thickness, surface texture and porosity, ambient and surface temperatures, humidity, and if the product is being used as a cure coat or a seal coat.

At 70°F, approximate dry times:

Tack free:	1 hour
Light foot traffic:	6 hours
Light car traffic:	24 hours
Normal car traffic:	72 hours

**8. Maintenance:** Periodically inspect cured and sealed surfaces for wear or damage. All concrete curing and sealing compounds will eventually exhibit the affects of weathering and traffic. For maximum coating life and performance, wipe up all chemical solvent or petroleum spills as soon as possible. Remove abrasive debris by sweeping or vacuuming. Do not drag, drop or place sharp edges on sealed surfaces. Periodic washings with mild detergents will help maintain surface luster. Do not use solvent or acid-

based cleaning materials for general cleaning. Hot car tires or turning tires while car is stationary may damage the sealer. Surfaces that will be subjected to car traffic, de-icing salts or chemical exposure, must receive minimally, two applications of Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal.

Prior to re-coating, the surface and joints must be clean, dry, free from cleaning product residue, other contamination, or loose materials, which will affect the adhesion of Clear Guard® H<sub>2</sub>O PLUS+ Water-Based Cure and Seal. When re-coating, a slip resistant additive must be added to the sealer.

**8.1. INTERIOR FLOORS:** Regularly clean by dry and wet mopping. Periodically machine scrub, rinse, and wet vacuum the surface. Apply a maintenance wax or slip resistant wax as directed by the wax manufacturer. This type of periodic maintenance will greatly enhance the appearance of the floor and minimize the need to strip and/or reapply the sealer.

**9. Quality Control:** Cast a job site sample at least 21 days prior to the

installation for approval of color and finish. Utilize all materials, tools, and techniques from the actual job in the mock-up. Consistent batching, pouring, finishing, curing, sealing, and preparation techniques, will ensure the uniformity of architectural concrete. Verify adequate wet and dry slip resistance. Verify maintenance requirements. Site visits by Butterfield Color, Inc. Personnel are for making technical recommendations only and not for supervising or providing quality control.

**KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR PROFESSIONAL USE ONLY.**

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, in U.S. call CHEMTREC at 1-800-424-9300, International 703-741-5970, in Canada call CANUTEC (collect) 613-996-6666.

Prior to use of any Butterfield Color, Inc. product, the user must always read and follow the warnings and instructions on

the product's most current Technical Data Sheet, product label and Safety Data Sheet which are available online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) or at 800-282-3388. Nothing contained in any Butterfield Color, Inc. materials relieves the user of the obligation to read and follow the warnings and instruction for each Butterfield Color, Inc. product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use.

**LIMITED WARRANTY AND DISCLAIMER – EXCLUSIVE REMEDY:** Butterfield Color, Inc. (“BC”) warrants that this product conforms to its published specifications when it is shipped. THIS LIMITED WARRANTY IS THE EXCLUSIVE WARRANTY AND THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. BC does not warrant any particular method of use or application of the product or its performance under any particular condition. If this product does not conform to its published specifications when shipped, we will replace the product as your exclusive remedy. Any action for breach of the limited warranty or any other liability arising from this product must be brought within 90 days of receiving the product. BC is not liable for consequential damages or personal injury arising from the use, storage or handling of this product.